



Description

STRONG THREADLOCKERS

Details

To lock, studs, nuts and bolts not requiring disassembly. Low viscosity product. It eliminates loosening due to vibrations, impacts, sudden changes in temperature. It prevents corrosion and seizing. Permanent locking

PHYSICAL-CHEMICAL AND TECHNICAL PROPERTIES

Properties	Description
Metacrylic Resin Appearance	Green
Specific weight	1.06 kg/l
Viscosity	300/500 mPa.s
Unscrewing torque ISO 10964	45/55 N/mm ²
Residual unscrewing torque	40/50 N/mm ²
Flash point	>100°C
Maximum Slack	0.25mm
Temperature resistance	-50>+150°C

Chemical resistance	T°C	100h	500h	1000h
Water/glycol	85	100	90	90
Brake liquid	22	100	90	90
Motor oil	125	100	90	90
Acetone	22	100	90	90

Important notes

Speed of polymerisation

This is influenced by the nature of the materials and the temperature at which the reaction occurs. The ideal temperature for polymerisation is between 20°C and 25°C. Lower temperatures slow down the reaction, whereas higher temperatures speed it up.

Recommendations for use

Clean the parts, apply over the entire surface involved. Tighten completely. Do not reposition the joints, and wait for it to harden for the required time. On passivated metal surfaces use together with the Activator P730.

N.B.: Not suitable for metal-plastic bonds, in oxygen circuits or to seal systems with strongly oxidizing alkaline or acid products. Shelf-life: 12 months at a temperature between +5°C and 28°C.

Packaging available

10-50ml

The information in this technical sheet is based on the specifications and potential use known to us. However, this data does not imply any legal obligation or liability whatsoever.

REGISTERED OFFICE
Via Domenico Scarlatti, 26
20124 Milan



Commercial Offices and Plant
Corso Europa, 91 – 20020 Solaro (MI)
info@farmicol.com
Customer Service +39 02 84505409
www.faren.com