



Description

SILICONE PAINT

Special silicone enamel paint, heat resistant up to 600°C
Available colours: Aluminium and Black. (Black resists up to 300° C)

Details

Product specifications

Product specifications

RAPID DRYING

HIGH ADHESIVE GRIP

Physical-Chemical Properties

Colour and Appearance Liquid

Specific weight 0.75 +/- 0.80 kg/l

Fragrance Typical solvent

Pressure at 20°C 4.0 +/- 0.5 bar

Thickness 1 coat 11 micron

Thickness 2 coats 30 micron

Pressure at 50°C 8.0 +/- 0.5 bar

Ford 4 Viscosity cup From 10.8 to 11"

Gran. on Grindometer From 0 to 2 micron

Gloss Shine grade From 8 to 85 Gloss

Drying time Dust free: 10 minutes

INSTRUCTIONS

- Apply on clean, dry surfaces.
- Vigorously shake the canister for one minute upside down.
- Spray thinly from a distance of approximately 20-30 cm.
- Wait a few minutes before repeating the treatment in the opposite direction (vertical-horizontal)

Recommendations for use

APPLICATIONS

- STOVES
- HEATING SYSTEMS
- ENGINE PARTS
- EXHAUST MANIFOLDS
- OVENS
- RADIATORS

N.B.:

- To dry completely/resist high temperatures, the paint will have to passivate for two days, after which it will gradually increase 50°C "steps" each time, to reach its ideal resistance up to a temperature of 300°C.
- Metric yield: 2m²/400ml canister

Packaging available

400ml

The information in this technical sheet is based on the specifications and potential use known to us. However, this data does not imply any legal obligation or liability whatsoever.

REGISTERED OFFICE
Via Domenico Scarlatti, 26
20124 Milan



Commercial Offices and Plant
Corso Europa, 91 – 20020 Solaro (MI)
info@farmicol.com
Customer Service +39 02 84505409
www.faren.com